

P.O. Box 84 Sherman, TX 75090 6412 Hwy 75 South Sherman, TX 75090

(903) 868-7111

Texas Instruments Enhanced Plastic Products Reliability Report

(Subject To Attached Disclaimers)

Device Type/Device Family: SN74LVTH16245AMDLREP

Package Type: 48/DLR
Wafer Fabrication Facility: Freising
Assembly/Test Facility: MLA
Compiled: 05/12

Biased Life Test

Test Method: JESD22-A108

Test Condition: 125°C / 1000 hours or equivalent

Sample Size: 5706 Rejects: 0

Activation Energy (eV): 0.7 Equivalent Device Hours: 6.50E+08 Failure Rate (FIT)*: 1.41

*Derated to +55°C with a 60% Confidence Level

Package Related Tests

<u>Description</u>	<u>Condition</u>	Referenced Method	Sample Size	Rejects	
Biased Humidity or	85°C / 85% / 1000 hours or	JESD22-A101	231	0	*
HAST	130°C / 85% / 96 hours	JESD22-A110			
Autoclave	121°C @ 2 atmospheres absolute for 96 hours	JESD22-A102	231	0	*
Temperature Cycle	-65°C to +150°C non-biased for 500 cycles or equivalent	JESD22-A104	231	0	*
High Temp Storage	150°C / 1,000 hours	JESD22-A103-A	231	0	*

^{*} Preconditioning per JEDEC Std. 22, Method A112/A113

Initial Product Qualification

The subject Enhanced Plastic device, device family, and/or package family have passed Texas Instruments product qualification as follows:

<u>Description</u>	<u>Condition</u>	Referenced Method	Sample Size	
Electrical Characterization	TI Data Sheet	N/A	3 lot(s)/90 Units	
Electrostatic Discharge Sensitivity	HBM MM CDM	EIA/JESD22-A114 EIA/JESD22-A115 JESD22-C101	3 Units/voltage N/A N/A	
Latch-up	Per Technology	EIA/JESD78	0/0	
Physical Dimensions	TI Data Sheet	EIA/JESD22- B100	0/0	
Thermal Impedance	Theta-JA on board	EIA/JESD51	Per Pin-Package	
Bias Life Test	125°C / 1000 hours or equivalent	JESD22-A108	0/0	
Biased Humidity or	85°C / 85% / 1000 hours or	JESD22-A101	156/0	*
HAST	130°C / 85% / 96 hours	JESD22-A110		
Autoclave	121°C @ 2 atmospheres absolute for 96 hours	JESD22-A102	276/0	*
Temperature Cycle	-65°C to +150°C non-biased for 500 cycles or equivalent	JESD22-A104	231/0	*
High Temp Storage	150°C / 1,000 hours	JESD22-A103-A	231/0	*
Solder Heat	260°C for 10 seconds	JESD22-B106	0/0	
Solderability	Condition A (steam age for 8 hours)	ANSI/J-STD-002-92	0/0	
Bond Strength	-	ASTM F-459	15/1	
Moisture Sensitivity	Surface Mount Only	J-STD-020-A	4/0	

^{*} Preconditioning per JEDEC Std. 22, Method A112/A113

Suplemental Device Characteristics

Master Die: RLVTH16245BIM Wafer Fab: Freising Fab Process: ASL2BSE Fab Technology: BiCMOS Die Revision: B Passivation: 7KACN

Metal 1: TiW/Al-Cu2 Metal 2: TiW/Al-Cu2 Assembly Site: MLA
Pin/Package Type: 48/DL
Lead Composition: Cu
Lead Finish: NiPdAu
Mount Compound Hitabi Fa

Mount Compound: Hitachi En-4088Z Bond: Au/24.3Um Mold Compound: Gr825-73B Die Thickness: 10.5 mils

Quality and Reliability Data Disclaimer

The attached quality and reliability information is specific to the TI Enhanced Plastic product family of plastic encapsulated commercial-off-the-shelf (COTS) semiconductor products and components. Due to possible differences in product assembly and test baselines, this information is NOT APPLICABLE to TI standard, industrial, or automotive catalog commercial products.

Plastic encapsulated TI semiconductor devices are not designed and are not warranted to be suitable for use in some military applications and/or military environments. Use of plastic encapsulated TI semiconductor devices in military applications and/or military environments, in lieu of hermetically sealed ceramic devices, is understood to be fully at the risk of Buyer.

Quality and reliability data provided by Texas Instruments is intended to be an estimate of product performance based upon history only. It does not imply that any performance levels reflected in such data can be met if the product is operated outside the conditions expressly stated in the latest published data sheet for a device.

Existing industry standards for plastic encapsulated microcircuit qualification and reliability monitors are based upon historical data, experiments, and field experience with the use of these devices in commercial and industrial applications. The applicability of these standards in determining the suitability for use and safety performance in military and aerospace applications has not been established. Due to the multiple variations in field operating conditions, a component manufacturer can only base estimates of product life on models and the results of package and die level qualification.

The buyer's use of this data, and all consequences of such use, is solely the buyer's responsibility. Buyer assumes full responsibility to perform sufficient engineering and additional qualification testing in order to properly evaluate the buyer's application and determine whether a candidate device is suitable for use in that application. The information provided by TI shall not be considered sufficient grounds on which to base any such determination.

THIS INFORMATION IS PROVIDED "AS IS" WITHOUT ANY EXPRESS OR IMPLIED WARRANTY OF ANY KIND INCLUDING WARRANTIES OF MERCHANTABILITY, NONINFRINGEMENT OF INTELLECTUAL PROPERTY, OR FITNESS FOR ANY PARTICULAR PURPOSE. IN NO EVENT SHALL TI OR ITS SUPPLIERS BE LIABLE FOR ANY DAMAGES WHATSOEVER (INCLUDING, WITHOUT LIMITATION, DAMAGES FOR LOSS OF PROFITS, BUSINESS INTERRUPTION, LOSS OF INFORMATION) ARISING OUT OF THE USE OF OR INABILITY TO USE THE INFORMATION, EVEN IF TI HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGES.

THIS INFORMATION SHOULD NOT BE USED TO ASSIST IN THE PRACTICE OF "UPRATING" OR "UPSCREENING" DEVICES FOR USE BEYOND THEIR RATED LIMITS.

TI may provide technical, applications or design advice, quality characterization, and reliability data or service providing these items shall not expand or otherwise affect TI's warranties as set forth in the Texas Instruments Incorporated Standard Terms and Conditions of Sale for Semiconductor Products and no obligation or liability shall arise from TI's provision of such items.

Quality and Reliability Data copyright © 2002, Texas Instruments Incorporated, all rights reserved.

IMPORTANT NOTICE

Texas Instruments Incorporated and its subsidiaries (TI) reserve the right to make corrections, modifications, enhancements, improvements, and other changes to its products and services at any time and to discontinue any product or service without notice. Customers should obtain the latest relevant information before placing orders and should verify that such information is current and complete. All products are sold subject to TI's terms and conditions of sale supplied at the time of order acknowledgment.

TI warrants performance of its hardware products to the specifications applicable at the time of sale in accordance with TI's standard warranty. Testing and other quality control techniques are used to the extent TI deems necessary to support this warranty. Except where mandated by government requirements, testing of all parameters of each product is not necessarily performed.

TI assumes no liability for applications assistance or customer product design. Customers are responsible for their products and applications using TI components. To minimize the risks associated with customer products and applications, customers should provide adequate design and operating safeguards.

TI does not warrant or represent that any license, either express or implied, is granted under any TI patent right, copyright, mask work right, or other TI intellectual property right relating to any combination, machine, or process in which TI products or services are used. Information published by TI regarding third-party products or services does not constitute a license from TI to use such products or services or a warranty or endorsement thereof. Use of such information may require a license from a third party under the patents or other intellectual property of the third party, or a license from TI under the patents or other intellectual property of TI.

Reproduction of TI information in TI data books or data sheets is permissible only if reproduction is without alteration and is accompanied by all associated warranties, conditions, limitations, and notices. Reproduction of this information with alteration is an unfair and deceptive business practice. TI is not responsible or liable for such altered documentation. Information of third parties may be subject to additional restrictions.

Resale of TI products or services with statements different from or beyond the parameters stated by TI for that product or service voids all express and any implied warranties for the associated TI product or service and is an unfair and deceptive business practice. TI is not responsible or liable for any such statements.

TI products are not authorized for use in safety-critical applications (such as life support) where a failure of the TI product would reasonably be expected to cause severe personal injury or death, unless officers of the parties have executed an agreement specifically governing such use. Buyers represent that they have all necessary expertise in the safety and regulatory ramifications of their applications, and acknowledge and agree that they are solely responsible for all legal, regulatory and safety-related requirements concerning their products and any use of TI products in such safety-critical applications, notwithstanding any applications-related information or support that may be provided by TI. Further, Buyers must fully indemnify TI and its representatives against any damages arising out of the use of TI products in such safety-critical applications.

TI products are neither designed nor intended for use in military/aerospace applications or environments unless the TI products are specifically designated by TI as military-grade or "enhanced plastic." Only products designated by TI as military-grade meet military specifications. Buyers acknowledge and agree that any such use of TI products which TI has not designated as military-grade is solely at the Buyer's risk, and that they are solely responsible for compliance with all legal and regulatory requirements in connection with such use.

Applications

TI products are neither designed nor intended for use in automotive applications or environments unless the specific TI products are designated by TI as compliant with ISO/TS 16949 requirements. Buyers acknowledge and agree that, if they use any non-designated products in automotive applications, TI will not be responsible for any failure to meet such requirements.

Following are URLs where you can obtain information on other Texas Instruments products and application solutions:

Products

OMAP Mobile Processors www.ti.com/omap

Wireless Connectivity

Audio	www.ti.com/audio	Automotive and Transportation	www.ti.com/automotive
Amplifiers	amplifier.ti.com	Communications and Telecom	www.ti.com/communications
Data Converters	dataconverter.ti.com	Computers and Peripherals	www.ti.com/computers
DLP® Products	www.dlp.com	Consumer Electronics	www.ti.com/consumer-apps
DSP	dsp.ti.com	Energy and Lighting	www.ti.com/energy
Clocks and Timers	www.ti.com/clocks	Industrial	www.ti.com/industrial
Interface	interface.ti.com	Medical	www.ti.com/medical
Logic	logic.ti.com	Security	www.ti.com/security
Power Mgmt	power.ti.com	Space, Avionics and Defense	www.ti.com/space-avionics-defense
Microcontrollers	microcontroller.ti.com	Video and Imaging	www.ti.com/video
RFID	www.ti-rfid.com		

www.ti.com/wirelessconnectivity

TI E2E Community Home Page

e2e.ti.com